

## Base coat for EIFS/ETICS

### Guide Formulation

---

Mineral base mixture	Parts by Weight
Portland cement	20-30
Limestone flour < 0,1 mm	5- 10
Limestone or quartz sand 0,1 - 0,5 mm	60-70

---

Additives	Parts by Weight
KimaCell Cellulose ether	0,15- 0,25
Redispersible Polymer powder	2-4

---

Optimizing additives	Parts by Weight
Hydrophobing agent (stearate/oleate)	0.15-0.25
Fibres	0.2-0.4
Calcium formate	0.3-0.8